CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2007
DateRun:	10/03/2007
Experimenters:	Shweta Bansal
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Plastic
PartType:	Coupon
Contaminants:	Coatings
Cleaning Methods:	Manual Wipe
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: Spray cleaner on the coupons 30 secs Manual Wipe cleaning at 130 F Drying: wipe Contaminant Heraeus Covercoat L-406 Clear Substrate 2"x 4"x 0.06" Polycarbonate Plastic Coupons
Results:	
Summary:	

Substrates:	Plastic				
Contaminants:	Coatings				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Bio Chem Systems	Bio T Max	5	-35.00	☐	
Transene Company, Inc.	D Greeze 500 LO	5	-56.10	☐	
21st Century Composites	Envirosolve	100	-5.17	☐	

Conclusion: No product removed the coating using manual wiping.