

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2008
 DateRun: 09/22/2008
 Experimenters: Jason Marshall
 ClientType: Machine Construction Company
 ProjectNumber: Project #2
 Substrates: Steel
 PartType: Coupon
 Contaminants: Coatings
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric

Purpose: To evaluate top two products on supplied contaminant using heated immersion cleaning.

Experimental Procedure: The top two products were selected from the previous trial based on success on removing the first supplied soil using heated immersion cleaning. Both were used at full strength based on vendor recommendations. Beakers were heated to 130 F on a hot plate. Six preweighed steel coupons were coated with the rust preventative VCI 368 using a hand held swab. Coupons were weighed again to determine the amount of soil added. Three coupons were cleaned in each solution for 10 minutes using stir bar agitation. Coupons were rinsed for 15 seconds in tap water at 120 F and dried using compressed air at room temperature for 30 seconds. Final weights were recorded and efficiencies calculated.

Results: Both products removed over 90% of the VCI 368 contaminant using heated immersion cleaning. The table lists the amount of soil added, the amount remaining and the efficiency for each coupon cleaned.

Cleaner	Initial wt	Final wt	% Removed
Smart Solve 605			
	0.3991	0.0279	93.01
	0.2898	0.0252	91.30
	0.2886	0.0283	90.19
Bean-e-doo			
	0.2358	0.0277	88.25
	0.5005	0.0302	93.97
	0.2993	0.0253	91.55

Summary:

Substrates:	Steel				
Contaminants:	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
United Laboratories International	Smart Solve 605	100	91.50	<input checked="" type="checkbox"/>	
Franmar Chemical	Bean-e-doo (Parts Washer Solvent)	100	91.26	<input checked="" type="checkbox"/>	

Conclusion: The same two products will be evaluated on the next supplied contaminant (VCI 325) using heated immersion cleaning.