

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2008
DateRun: 11/04/2008
Experimenters: Johanna Oviedo
ClientType: Lab
ProjectNumber: Project #1
Substrates: Stainless Steel
PartType: Coupon
Contaminants: Oil
Cleaning Methods: Immersion/Soak
Analytical Methods: Gravimetric

Purpose: To test nontoxic industrial cleaning solution for oil removal.

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Products were selected based in the compatibility of substrate and removal of foreign substance. Used 10% of concentration and heated the samples at 135 F. The coupons were immersed in a product for 5 minutes, dried in 30 seconds using compressed air is room temperature. The contaminated coupons were weighed again to determine the amount of soil added. After cleaning process, the final weights were recorded, efficiencies were calculated and recorded.

Cleaner	Initial wt	Final wt	% Removed
Kyzen Corporation Optisol Op7432			
	0.5136	0.4399	14.36
	0.3518	0.1498	57.42
	0.2410	0.0542	77.51
Kyzen Corporation Optisol Op7168			
	0.5370	0.2175	59.50
	0.3416	-0.0283	108.28
	0.3664	-0.0275	107.51
Brulin Corporation, Metalnox			
	0.1288	0.0088	93.17
	0.1883	0.0096	94.90
	0.1045	0.0059	94.35

Summary:		Substrates: Stainless Steel			
		Contaminants: Oil			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Kyzen Corporation	Optisolv OP7432	10	49.76	<input type="checkbox"/>	
Kyzen Corporation	Optisolv OP7168	10	91.76	<input checked="" type="checkbox"/>	
Brulin Corporation	Compliance	10	94.14	<input checked="" type="checkbox"/>	

Conclusion: The Optisol Op7432 cleaned better than the others.