

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2005
 DateRun: 08/16/2005
 Experimenters: Jason Marshall
 ClientType: Cleaner Manufacturer
 ProjectNumber: Project #1
 Substrates: Glass/Quartz, Chrome
 PartType: Coupon
 Contaminants: Films, Soaps
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric

Purpose: To evaluate supplied product on two substrates for glass soap scum removal.

Experimental Procedure: The supplied cleaning product was diluted to vendor recommended concentration for glass cleaning. The product was diluted with DI water.

Three preweighed chrome and three glass coupons were coated with SSL Soil 2 (Glass soap scum: Colgate Regular shaving cream 5.3%, Arid Extra Extra Spray Deodorant 3.5%, Suave Naturals Flexible Hold hair spray 3.7%, Aleeda Texurizing hair gel 25.6% Colgate Total toothpaste 10.4%, Water 51.5%) by pump spraying the mix. The soil was allowed to dry for 24 hours at room temperature. The contaminated coupons were weighed again to determine the amount of soil added.

Three coupons were placed into a Gardner Straight Line Washability unit. A Professional Painter's Rag was attached to the cleaning sled and soaked with 5-7 sprays of cleaning solutions. Each coupon was sprayed 7-10 times with the same cleaning solution. The cleaning unit was run for 5 cycles (~9 seconds). At the end of the cleaning, coupons were wiped once with a dry paper towel. Final weights were recorded, efficiencies were calculated and recorded.

Results: The supplied product removed over 90% of the soil from the two substrates. The table below lists the amount of soil applied and removed from the coupons.

Cleaner	Initial wt	Final wt	% Removed
DFC 23 Glass	0.0354	0.0037	89.55
	0.0583	0.0040	93.14
	0.0208	0.0028	86.54
DFC 23 Chrome	0.0430	0.0079	81.63
	0.0567	0.0012	97.88
	0.0911	0.0037	95.94

Summary:

Substrates:	Glass/Quartz, Chrome				
Contaminants:	Films, Soaps				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Cogent Environmental Solutions	DFC 23	0.4	90.78	<input checked="" type="checkbox"/>	

Conclusion: The overall efficiency of the glass cleaner was 90.78, passing the cut off of 85%.