

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2005  
DateRun: 09/15/2005  
Experimenters: Jason Marshall  
ClientType: Environmental Service Firm  
ProjectNumber: Project #1  
Substrates: Wood  
PartType: Coupon  
Contaminants: Coatings  
Cleaning Methods:  
Analytical Methods: Performance Test  
Purpose: To evaluate impact resistance for sealer and coating combined.

Experimental Procedure: The moisture content at the time of testing will influence results due to the hygroscopic nature of the base materials. Therefore, efforts must be taken to ensure that the moisture content and temperature remain constant during the evaluation period. Ideally, the sample floor should be kept at 65+/-1% relative humidity and 68+/-6 F.

During laboratory testing, conditions were slightly drier, 40% relative humidity, but the temperature was within the given temperature range ~70 F).

## Sample Preparation

The flooring material supplied was Hardwood flooring made from Red Oak. The boards were ¾" thick, 2 ¼" wide and cut into 8" sections. Some pieces of the flooring had to be sanded prior to making initial thickness readings to remove residual packing tape adhesive. With the boards cut into 8" coupons, three readings were made using a Brown & Sharpe Micrometer to measure each coupon's initial board thickness. Each reading was made to 0.001" and the three values were averaged to give a baseline thickness for the coupons. In addition to the thickness baseline, baselines were established for Gloss, Coefficient of Friction, Impact, Small Area Loads. Procedures for each baseline measurement followed the procedures to be outlined.

Following the establishment of the baselines, three coupons were coated with a supplied floor finish according to the manufacturers' specifications. The finish was applied using a 1" Pure Bristle 1500 paint brush. To ensure consistent coating application, the finish was leveled off using a 10 mils Precision Gage & Tool Co Dow Film Caster. Three coats were used for each floor finish as this was common number of coating layers suggested by the various manufacturers. Each coating layer was allowed to dry for 2 hours prior to the application of the next coat. Completed coupons were allowed to sit for a minimum period of 24 hours before performance evaluations were conducted.

## Falling-Ball Indentation

This test is designed to obtain a measure of the resistance of a flooring finish to impacts from dropped objects. Four drops were made for each coupon for a total of twelve drops per finish. Each drop was made at 6" intervals starting at 6" and ending at 72". The ball used for the drops was a 440-C stainless steel 2" diameter ball, grade 100.

The same Brown & Sharpe Micrometer was used to measure the indentations to the coated coupons. A plot was made of the height of drop and residual indentation and the slope of the best fit line was calculated. From the plots, the intercept of the height of drop at 72" was recorded as the index of indentation resistance. Results for each finish were compared each other.

Results: Impact depth was calculated by subtracting the average initial coating thickness from the thickness measured at the point of impact for each drop height. The initial average coating thickness was calculated from the three initial coating measurements made for each coupon.

	Coated Thickness			Drop Height											
Coupon	Middle	End 1	End 2	6	12	18	24	30	36	42	48	54	60	66	72
d	7.551	7.580	7.578				7.207								
d Alt	6.849	6.879	6.892	6.568	6.606	6.600									
e	7.600	7.536	7.612					7.486	7.518	7.439	7.327				
e Alt	6.887	6.900	6.909												
f	7.542	7.608	7.543												7.304
f Alt	6.815	6.910	6.952									6.495	6.410	6.380	
	Coated Thickness			Drop Height											

# CLEANING LABORATORY EVALUATION SUMMARY

Coupon	Middle	End 1	End 2	6	12	18	24	30	36	42	48	54	60	66	72
d	7.551	7.580	7.578				7.207								
e	7.600	7.536	7.612					7.486	7.518	7.439	7.327				
f	7.542	7.608	7.543												7.304
Coated Thickness				Drop Height											
Coupon	Middle	End 1	End 2	6	12	18	24	30	36	42	48	54	60	66	72
d Alt	6.849	6.879	6.892	6.568	6.606	6.600									
e Alt	6.887	6.900	6.909												
f Alt	6.815	6.910	6.952									6.495	6.410	6.380	

\*Due to the construction of the floor boards and the location of the impact from the ball, additional baseline readings had to be recorded for certain areas on the coupons. These values are designated by the coupon number and Alt (alternate).

	Drop Height											
	6	12	18	24	30	36	42	48	54	60	66	72
Pro Finisher Sealer + Polyurethane	0.305	0.267	0.273	0.363	0.097	0.065	0.144	0.256	0.397	0.482	0.512	0.260

## Comparison

Uncoated		0.196	
Product	Slope of Best Fit Line	Index of Indentation Resistance	Rank
Polyurethane Gloss	263.41	0.273	2
WB Polyurethane	217.66	0.331	3
WB Sanding Sealer	205.34	0.351	4
Aqua Deva Metro	277.07	0.260	1
Hydro 202 Satin	137.7	0.523	8
SafeCoat Satin	148.69	0.484	5
SafeCoat Gloss	141.73	0.508	7
Kiilto Lacquer	145.18	0.496	6
Kiilto Lacquer + Primer	132.63	0.543	9
Pro Finisher Water Based Sanding Sealer & Polyurethane	121.85	0.591	10

Summary:

Conclusion:

The index of indention for the combined sealer and coating was higher than either of the two products alone.